1109-1240/4





Application:



stone guard

Key Features:

· Can be used on all Glasurit PU and EP CV primer fillers and fillers

high flexible

· outstanding application characteristics

Remarks:

The substrate should be clean, free of dust, rust, oil and grease.

Substrates Glasurit CV - Primer Filler Anodized Aluminium Glasurit CV - Primer **Salvanized steel** Powder coating Staineless steel **OEM-Paintwork** old paint work coil-coating Aluminium = Very well suited **3RP / SMC** PP-EPDM Plywood = well suited Wood = suited in some cases



Spreading rate 379 m²/l at 1 μm

Solid Content ~ 53 %

Handling



Protect from frost.

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 μm .

The products are suitable for professional use only.

2004/42/IIB (e)(840)32: The EU limit value for this product (product category: IIB.e) in ready to

use form is max. 840 g/l. The VOC content of this product is 32 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

1109-1240/4



1109-1240/4 Variant Stone Chip protection

1		1
Ι.	_	ı
l.		ı

Mixing Ratio

max. 5% DE-water

Application:		Compliant - gravity feed cup	HVLP spray gun	Suction cup	Airless/ Air- mix	Pressure pot dblpump
Application pressure	bar	2-2.5		2-2.5	2-4	2.5
Material pressure	bar				120-180	2
Nozzle size		3-4		3-5	0.41-0.5	3-4
Number of coats		1-2		1-2	1-2	1-2
Film thickness	μm	40-50				

/ <	\rightarrow
()	7
7	$\overline{}$

Drying Overcoatable Tack-free Ready for masking Ready to assemble Sandable

Min. Max.

6 h

Object Temp. 20 °C

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 μm .

The products are suitable for professional use only.

2004/42/IIB (e)(840)32: The EU limit value for this product (product category: IIB.e) in ready to

use form is max. 840 g/l. The VOC content of this product is 32 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.