1109-1503/3





Application:

structure effect, stone guard, underbody protection

Key Features:

· high flexible

· can be used on all Glasurit PU and EP CV primer fillers and fillers

· outstanding application characteristics

Remarks:

The substrate should be clean, free of dust, rust, oil and grease.

Substrates									Filler						
 = Very well suited = well suited = suited in some cases 	Steel	Galvanized steel	Staineless steel	Aluminium	Anodized Aluminium	GRP / SMC	PP-EPDM	Glasurit CV - Primer	Glasurit CV - Primer Fil/ Filler	Powder coating	Coil-coating	Plywood	Wood	OEM-Paintwork	Old paint work



Spreading rate 395 m²/l at 1 µm

Solid Content $\sim 56 \%$

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 μm .

The products are suitable for professional use only.

2004/42/IIB (e)(840)25: The EU limit value for this product (product category: IIB.e) in ready to

use form is max. 840 g/l. The VOC content of this product is 25 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

1109-1503/3



Stone Chip and Underbody protection, grey

Handling



Protect from frost.



Can be thinned with 3% water if required.

Application:		Compliant - gravity feed cup	HVLP spray gun	Suction cup	Airless/ Airmix	Pressure pot dblpump
Application pressure	bar	2-2.5		2-2.5	2-4	2
Nozzle pressure	bar				120-180	2.5
Nozzle size		3-4		3-5	0.41-0.5	3-4
Number of coats		2-6		4-6	2-6	2-6
Film thickness	μm	500-1000				

\bigcirc	Drying	Overcoatable	Tack-free	Ready for masking Ready to assemble	Sandable	
		Min. Max.				
	Object Temp. 20°C	6 h				

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 μm .

The products are suitable for professional use only.

2004/42/IIB (e)(840)25: The EU limit value for this product (product category: IIB.e) in ready to

use form is max. 840 g/l. The VOC content of this product is 25 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.