



A brand of BASF –
We create chemistry

284-10

Glasurit CV transparent sealer

Application:



sign writing, cabs (color change), multi - color painting, powder coated profiles / boxes

Key Features:

- tintable
- brilliant top coat appearance
- fast drying

Remarks:

The substrate should be clean, free of dust, rust, oil and grease.

Substrates

- = Very well suited
- = well suited
- = suited in some cases

Steel	Galvanized steel	Stainless steel	Aluminium	Anodized Aluminium	GRP / SMC	PP-EPDM	Glasurit CV - Primer	Glasurit CV - Primer Filler / Filler	Powder coating	Coil-coating	Plywood	Wood	OEM-Paintwork	Old paint work
●●	●●	●●	●●	●●	○	●●	●●	●●	●●	●●	○	●●	●●	●●



Spreading rate 406 m²/l at 1 µm

Solid Content ~ 66 % (RFU~53%)

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

2004/42/IIIB (c II)(540)502: The EU limit value for this product (product category: IIB.c II) in ready to use form is max. 540 g/l. The VOC content of this product is 502 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

284-10

Glasurit CV transparent sealer



A brand of BASF –
We create chemistry



Mixing Ratio **2:1+30 % by volume**



Hardener 922-18 Pro, -16 Pro



Reducer 352-310, -315, -320



Spray viscosity at 20°C DIN 4: 17 s

Potlife at 20°C 3 h

Application:	Compliant - gravity feed cup	HVLV spray gun	Suction cup	Airless/ Airmix	Pressure pot dbl.-pump
Application pressure	2.2-2.5 bar	2 bar	2.5 bar		
Nozzle size	1.4	1.5	1.7		
Number of coats	1	1	1		
Film thickness	20-25 µm				



Drying	Overcoatable	Tack-free	Ready for masking	Ready to assemble	Sandable
	Min.	Max.			
Object Temp. 20°C	15 min	2 h			

Remark Transparent Sealer 284-10 can be tinted with (up to 10% of) 68 line topcoat.

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

2004/42/IIIB (c II)(540)502: The EU limit value for this product (product category: IIB.c II) in ready to use form is max. 540 g/l. The VOC content of this product is 502 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

284-10

Glasurit CV transparent sealer



A brand of BASF –
We create chemistry

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

2004/42/IIIB (c II)(540)502: The EU limit value for this product (product category: IIB.c II) in ready to use form is max. 540 g/l. The VOC content of this product is 502 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

BASF Coatings GmbH - Automotive Refinish Coatings Solutions Europe - Glasuritstrasse 1 - 48165 Münster - Germany

07/2023