


284-13

284-13 Variant with 568-17



A brand of BASF –
We create chemistry

Application:



chassis painting, container, construction machinery (steel), steel and galvanized steel spare parts

Remarks:

The substrate should be clean, free of dust, rust, oil and grease.
Aluminum-Chassis have to be primed with a suitable primer.
Use adhesion promoter 285-0CV after 8 h at 20°C or oven drying.
• 352-216, slow 15 - 20°C
• 352-345, very slow 20 - 25°C
• 352-370, extra slow 25 - 30°C

Substrates

- = Very well suited
- = well suited
- = suited in some cases

Steel	Galvanized steel	Stainless steel	Aluminium	Anodized Aluminium	GRP / SMC	PP-EPDM	Glasurit CV - Primer	Glasurit CV - Primer Filler / Filler	Powder coating	Coil-coating	Plywood	Wood	OEM-Paintwork	Old paint work
●●	●				●●		●●		●	●	●●	●●	●	●●

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

2004/42/IIIB (c I)(540)508: The EU limit value for this product (product category: IIB.c I) in ready to use form is max. 540 g/l. The VOC content of this product is 508 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

284-13

284-13 Variant with 568-17



A brand of BASF –
We create chemistry



Pre Mix

Premix 568-17 and reducer 1:1.
Replace max. 50% of the used reducer with 568-17.



Mixing Ratio

4 : 1 : 1 by volume



Hardener

922-18 Pro, -16 Pro



Reducer

352-216, -345, -370, -50, 568-17



Spray viscosity at 20°C

DIN 4: 25 s

Potlife at 20°C

30 min

Application:		Compliant - gravity feed cup	HVLV spray gun	Suction cup	Airless/ Airmix	Pressure pot dbl.-pump
Application pressure	bar	2.2-2.5	2	2.5		2.5
Material pressure	bar					0.8-1.5
Nozzle size		1.4	1.5	1.7		1-1.1
Number of coats		1.5	1.5	1.5		1.5
Flash off at 20°C	min	without	without	without		without
Film thickness	µm	40-60				

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

2004/42/IIIB (c I)(540)508: The EU limit value for this product (product category: IIB.c I) in ready to use form is max. 540 g/l. The VOC content of this product is 508 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

284-13

284-13 Variant with 568-17



A brand of BASF –
We create chemistry



Drying

Overcoatable

Tack-free

Ready for masking

Ready to assemble

Sandable

Object Temp. 20°C	Overcoatable		Tack-free	Ready for masking	Ready to assemble
	Min.	Max.			
	30 min	8 h	30 min	30 min	30 min

Remark

To plasticize the product, see variant with 522-111 softface additive.
 Can be overcoated with CV topcoats of Lines 68, 58, 55.
 For tinting see variant with CV Primer Tinting Paste 568-408.
 Mixing ratio 5:1:1 see variant for rough-blasted substrates.
 On hot-dip galvanized steel, adhesion must be tested beforehand.
 The area to be painted should not exceed 3 m².

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

2004/42/IIIB (c I)(540)508: The EU limit value for this product (product category: IIB.c I) in ready to use form is max. 540 g/l. The VOC content of this product is 508 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.