

284-45E

284-45E Variant with 568-17E Eco Balance CV multi color and drying additive



A brand of BASF –
We create chemistry

Application:



busses, plastic painting, cabs (color change), boxes, daylight fluorescent paint

Remarks:

The substrate should be clean, free of dust, rust, oil and grease.

Substrates

- = Very well suited
- = well suited
- = suited in some cases

Steel	Galvanized steel	Stainless steel	Aluminium	Anodized Aluminium	GRP / SMC	PP-EPDM	Glasurit CV - Primer	Glasurit CV - Primer Filler / Filler	Powder coating	Coil-coating	Plywood	Wood	OEM-Paintwork	Old paint work
					●●		●●	●●	●●	●●	●●	●●	●●	●●

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

2004/42/IIIB (c I)(540)456: The EU limit value for this product (product category: IIB.c I) in ready to use form is max. 540 g/l. The VOC content of this product is 456 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

284-45E

284-45E Variant with 568-17E Eco Balance CV multi color and drying additive



A brand of BASF –
We create chemistry



Pre Mix

Premix 568-17E and reducer 1:1.
Replace max. 50% of the used reducer with 568-17E.



Mixing Ratio

2:1 + 10% by volume



Hardener

922-180 Pro



Reducer

352-320E, -330, -310, -340, 568-17E



Spray viscosity at 20°C

DIN 4: 17-21 s

Potlife at 20°C

30 min

Application:	Compliant - gravity feed cup	HVLP spray gun	Suction cup	Airless/ Airmix	Pressure pot dbl.-pump
Application pressure	2.2-2.5 bar	2 bar	2.5 bar	2 bar	2.5 bar
Nozzle pressure					0.8-1.5 bar
Material pressure				120-150 bar	
Nozzle size	1.4-1.6	1.5	1.7	0.28-0.33	1-1.1
Voltage				50-80 kV	
Elect. Resistance				600-800 Ω	
Number of coats	1.5	1.5	1.5	1.5	1.5
Flash off at 20°C	without	without	without	without	without
Film thickness	50-70 µm				

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

2004/42/IIIB (c I)(540)456: The EU limit value for this product (product category: IIB.c I) in ready to use form is max. 540 g/l. The VOC content of this product is 456 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

284-45E

284-45E Variant with 568-17E Eco Balance CV multi color and drying additive



A brand of BASF –
We create chemistry



Drying

Overcoatable

Tack-free

Ready for masking

Ready to assemble

Sandable

Object Temp. 20°C	Min.	Max.	30 min	30 min	30 min
	30	8 h			

Remark

Can be tinted by adding up to 10% of 68 Line topcoat.
Sanded areas have to be overcoated within 8h with 68, 55 Line, otherwise the adhesion promoter 284-10 has to be used.
The area to be painted should not exceed 3 m².

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.



Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.
The products are suitable for professional use only.

2004/42/IIIB (c I)(540)456: The EU limit value for this product (product category: IIB.c I) in ready to use form is max. 540 g/l. The VOC content of this product is 456 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.