

284-45

284-45 Variant with 568-408



A brand of BASF –
We create chemistry

Application:



busses, plastic painting, cabs (color change), boxes, daylight fluorescent paint

Key Features:

- 284-45 white (greyscale 08)
- good adhesion to various plastics
- brilliant top coat appearance
- good leveling
- filler for daylight fluorescent paint and for 2 step colors
- tintable
- overcoatable with Glasurit topcoat Line 58, 68, 55

Remarks:

- The substrate should be clean, free of dust, rust, oil and grease.
- 352-216, slow 15 - 20°C
 - 352-345, very slow 20 - 30°C

Substrates

- = Very well suited
- = well suited
- = suited in some cases

Steel	Galvanized steel	Stainless steel	Aluminium	Anodized Aluminium	GRP / SMC	PP-EPDM	Glasurit CV - Primer	Glasurit CV - Primer Filler / Filler	Powder coating	Coil-coating	Plywood	Wood	OEM-Paintwork	Old paint work
					●●	●	●●	●●	●●	●●	●●	●●	●●	●●

Safety advice:

2004/42/IIIB (c I)(540)456: The EU limit value for this product (product category: II B.c I) in ready to use form is max. 540 g/l. The VOC content of this product is 456 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm

The products are suitable for professional use only.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

284-45

284-45 Variant with 568-408


 A brand of BASF –
We create chemistry

	Pre Mix	max. 10% 568-408 by volume
	Mixing Ratio	2:1 + 10 - 30% by volume
	Hardener	922-180 Pro
	Reducer	352-216, -345
	Spray viscosity at 20°C	DIN 4: 17-21 s
	Potlife at 20°C	1.5 h

Application:		Compliant - gravity feed cup		HVLV spray gun		Suction cup		Airless/ Airmix		Pressure pot dbl.-pump
Application pressure	bar	2.2-2.5	2	2.5	2	2.5				
Nozzle pressure	bar									0.8-1.5
Material pressure	bar						120-150			
Nozzle size		1.4-1.6	1.5	1.7	0.28-0.33	1-1.1				
Voltage	kV				50-80					
Elect. Resistance	Ω				600-800					
Number of coats		1.5	1.5	1.5	1.5	1.5				
Flash off at 20°C	min	without	without	without	without	without				
Film thickness	µm	50-70								

Safety advice:

2004/42/IIIB (c I)(540)456: The EU limit value for this product (product category: IIB.c I) in ready to use form is max. 540 g/l. The VOC content of this product is 456 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm

The products are suitable for professional use only.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

BASF Coatings GmbH - Automotive Refinish Coatings Solutions Europe - Glasuritstrasse 1 - 48165 Münster - Germany

11/2021

284-45

284-45 Variant with 568-408



A brand of BASF –
We create chemistry



Drying

	Overcoatable		Tack-free	Ready for masking	Ready to assemble	Sandable
	Min.	Max.				
Object Temp. 20°C	60 min	72 h	2 h	16 h	16 h	16 h
Object Temp. 60°C	30 min		30 min	30 min	30 min	45 min

Remark

Can be tinted by adding up to 10% of 68 line topcoat.

For sanding the filmthickness should be 80 µm (50 – 60 µm after sanding) and the drying time has to be 45 min 60°C or 16 h 20 °C. Sandthroughs have to covered by using a suitable primer.

Safety advice:

2004/42/IIIB (c I)(540)456: The EU limit value for this product (product category: IIB.c I) in ready to use form is max. 540 g/l. The VOC content of this product is 456 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm

The products are suitable for professional use only.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.