## 284-60





Application:





boxes, construction vehicles, silo / tank truck, bus

**Key Features:** 

- · can be used on many substrates
- greyshade L04 (tintable with max. 10% 568-408)
- very good corrosion protection
- good appearance used wet on wet
- · can be used for large areas

Remarks:

Suitable for commercial vehicle repair and aluminum add-on parts. Due to the large number of different aluminum alloys, the coating of large areas of vehicles (e. g. dropsides) or the close-to-production line coating of vehicles must be tested from a technological standpoint beforehand.

The substrate should be clean, free of dust, rust, oils and grease. The pre-treated metallic surface must be coated on the same day to prevent renewed oxidation.

### **Substrates**

- = Very well suited
- = well suited
- = suited in some cases

**Galvanized steel** Staineless steel

Aluminium

Anodized Aluminium **GRP / SMC** 

Glasurit CV - Primer

PP-EPDM

Glasurit CV - Primer Filler / Filler Powder coating

Coil-coating Plywood

**OEM-Paintwork** Old paint work

Spreading rate

444 m<sup>2</sup>/l at 1 µm

**Solid Content** 

~ 74% res. ~65% mixed (+/- 2%)

### Safety advice:

It cannot be ruled out that this product contains particles < 0.1  $\mu m.\,$ 

The products are suitable for professional use only.

2004/42/IIB (c I)(540)488: The EU limit value for this product (product category: IIB.c I) in

ready to use form is max. 540 g/l. The VOC content of this product is 488 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

## 284-60

Glasurit CV universal primer filler, grey





Mixing Ratio

4:1:1 by volume wet on wet

5:1:1 by volume sanding

Hardener

922-220 PRO



Reducer

352-315, -320, -330



Spray viscosity at 20°C

DIN 4: 18-20 s

Potlife at 20°C

1.5 h

Application:	Compliant - gravity feed cup	₩ HVLP spray gun	Suction cup	Airless/ Airmix	Pressure pot dblpump
Application pressure	2.2-2.5 bar	2 bar	2.5 bar	2 bar	2.5 bar
Nozzle pressure				120-150 bar	0.8-1.5 bar
Nozzle size	1.4-1.6	1.7	1.7	0.28-0.33	1-1.1
Voltage				50-80 kV	
Elect. Resistance				1300-1600 Ω	
Number of coats	2	2	2	2	2
Flash off at 20°C	10-15 min	10-15 min	10-15 min	10-15 min	10-15 min
Film thickness	50-70 μm				

#### Safety advice:

It cannot be ruled out that this product contains particles < 0.1  $\mu m$ .

The products are suitable for professional use only.

2004/42/IIB (c I)(540)488: The EU limit value for this product (product category: IIB.c I) in

ready to use form is max. 540 g/l. The VOC content of this product is 488 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

# 284-60





Drying	Overcoatable		Tack-free	Ready for masking	Ready to assemble	Sandable
	Min.	Max.				
Object Temp. 20°C	60 min	72 h	6 h	16 h	16 h	16 h
Object Temp. 60°C	30 r	min	30 min	30 min	30 min	45 min

Remark

On hot-dip galvanized steel, adhesion must be tested beforehand. For tinting see CV Primer Tinting Paste 568-408.

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

#### Safety advice:

It cannot be ruled out that this product contains particles < 0.1  $\mu m$ .

The products are suitable for professional use only.

2004/42/IIB (c I)(540)488: The EU limit value for this product (product category: IIB.c I) in

ready to use form is max. 540 g/l. The VOC content of this product is 488 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.