


568-M 135E

568-M 135E / 68-line variant with 568-407



A brand of BASF –
We create chemistry

Application:



all applications

Key Features:

- allows application of the top coat with brush or roller
- suitable on all Glasurit CV primer filler and filler
- good leveling

Remarks:

The substrate should be clean, free of dust, rust, oil and grease.

Substrates

- = Very well suited
- = well suited
- = suited in some cases

Steel	Galvanized steel	Stainless steel	Aluminium	Anodized Aluminium	GRP / SMC	PP-EPDM	Glasurit CV - Primer	Glasurit CV - Primer Filler / Filler	Powder coating	Coil-coating	Plywood	Wood	OEM-Paintwork	Old paint work
								●●						

Handling



2 - 3 applications with brush or roll. Intermediate drying 3 h 20°C.

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

2004/42/IIIB (d)(420)419: The EU limit value for this product (product category: IIB.d) in ready to use form is max. 420 g/l. The VOC content of this product is 419 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

568-M 135E

568-M 135E / 68-line variant with 568-407



A brand of BASF –
We create chemistry



Mixing Ratio 4:1 + 5 - 15% by volume



Hardener 922-138E, -139, -136



Reducer 568-407

Potlife at 20°C 1.5 h



Drying	Overcoatable		Tack-free	Ready for masking	Ready to assemble	Sandable
	Min.	Max.				
Object Temp. 20°C	3 h	16 h	2.5 h	16 h	12 h	16 h
Object Temp. 60°C	30 min		30 min	30 min	30 min	30 min

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.



Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

2004/42/IIIB (d)(420)419: The EU limit value for this product (product category: IIB.d) in ready to use form is max. 420 g/l. The VOC content of this product is 419 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.