
### 568-M 135





Application:





all applications

**Key Features:** 

- · good leveling
- · fast to assemble
- · quick-drying for multicolor painting with 68 line

Remarks:

The substrate should be clean, free of dust, rust, oil and grease.

Substrates									Filler						
<ul> <li>= Very well suited</li> <li>= well suited</li> <li>= suited in some cases</li> </ul>	Steel	Galvanized steel	Staineless steel	Aluminium	Anodized Aluminium	GRP / SMC	PP-EPDM	Glasurit CV - Primer	<ul><li>Glasurit CV - Primer Fil</li><li>/ Filler</li></ul>	Powder coating	Coil-coating	Plywood	Mood	O OEM-Paintwork	O Old paint work

#### Safety advice:

It cannot be ruled out that this product contains particles < 0.1  $\mu m$ .

The products are suitable for professional use only.

2004/42/IIB (d)(420)419: The EU limit value for this product (product category: IIB.d) in ready to use form is max. 420 g/l. The VOC content of this product is 419 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

# 568-M 135

568-M 135 / 68-line variant with 568-17





**Mixing Ratio** 

4:1:1 by volume



Hardener

922-138, -136



Reducer

568-17



Spray viscosity at 20°C

DIN 4: 18-22 s

Potlife at 20°C

30 min

Application:		Compliant - gravity feed cup	HVLP spray gun	Suction cup	Airless/ Airmix	Pressure pot dblpump
Application pressure	bar	2.2-2.5	2	2.5		2.5
Material pressure	bar					0.8-1.5
Nozzle size		1.3-1.4	1.5	1.7		1-1.1
Voltage	kV					50-80
Number of coats		1.5	1.5	1.5		1.5
Flash off at 20°C	min	without	without	without		without
Film thickness	μm	40-60				

$\bigcirc$	Drying	Overco	atable	Tack-free	Ready for masking	Ready to assemble	Sandable
	Object Temp. 20°C	Min. 30 min	Max. 8 h	30 min	30 min	30 min	

### Safety advice:

It cannot be ruled out that this product contains particles < 0.1  $\mu m$ .

The products are suitable for professional use only.

2004/42/IIB (d)(420)419: The EU limit value for this product (product category: IIB.d) in ready to use form is max. 420 g/l. The VOC content of this product is 419 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

## 568-M 135

568-M 135 / 68-line variant with 568-17



#### Remark

Pre-spray 1 light coat, then apply 1 wet coat for flow. The area to be painted should not exceed 3 m<sup>2</sup>.

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

#### Safety advice:

It cannot be ruled out that this product contains particles < 0.1  $\mu m$ .

The products are suitable for professional use only.

2004/42/IIB (d)(420)419: The EU limit value for this product (product category: IIB.d) in ready to use form is max. 420 g/l. The VOC content of this product is 419 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

BASF Coatings GmbH - Automotive Refinish Coatings Solutions Europe - Glasuritstrasse 1 - 48165 Münster - Germany