



TECHNICAL INFORMATION

839-45

Glasureit CV Flexible Body Filler
light grey

BF

Range of application:



all applications

Performance:

- suitable for large areas / surfaces
- high flexible alignment for welding seams
- long pot life
- temperature resistance up to 180°C

Special remarks:

It cannot be ruled out that this product contains particles < 0.1 µm
The products are suitable for professional use only.

2004/42/IIIB (b)(250)180: The EU limit value for this product (product category: IIB.b) in ready to use form is max. 250 g/l. **The VOC content of this product is 180 g/l.**

Substrates:

- = very well suited
- = well suited
- = suited in some cases

Steel	Galvanized steel	Stainless steel	Aluminium	Anodized Aluminium	GRP / SMC	PP-EPDM	Glasureit CV - Primer	Glasureit CV - Primer Filler / Filler	Powder coating	Coil-Coating	Plywood	Wood	OEM-PAint work	old paint work
●●			●●		●			●	●	●	●	●●	●	●

Remarks:



Painting process

Spreading rate

Solid content 98 %

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.



TECHNICAL INFORMATION

839-45 Glasurit CV Flexible Body Filler
light grey

BF



Mixing ratio 100 : 3



Hardeners 948-36



Reducer



Viscosity
DIN 4 / 20° C

Potlife 20 °C

20 min.



Drying



Over-coatable

min max



Tack-free



Ready for masking



Ready to assemble



Sandable

Object temp. 20°C

Object temp. 60°C

2,5 h

Remarks



Sandable after 2,5 hours.

Highly flexible product, for example for weld seams on tankers. Temperature resistant up to 180°C.

On zinc, before body-filling, EP 801-704 CV Primer Filler (30 - 40 µm, 30 min. 60°C) or 284-13 CV primer filler (20 - 25 µm, 20 min. 60°C) must be applied as adhesion promoter.

Do not use on wash primer or acid-pre-treated surfaces!