

839-7451

Glasurit CV body filler extra slow, light grey



A brand of BASF –
We create chemistry

- Application:** all applications
- Key Features:**
- to be used for large surfaces
 - high flexible alignment for welding seams
 - long potlife
 - suitable for high temperatures
- Remarks:** The substrate should be clean, free of dust, rust, oil and grease.

Handling

Substrates:

Very well suited:

- Steel
- Aluminium
- Wood



Well suited:

- GRP / SMC
- Glasurit CV Primer Filler / Filler
- Powder coatings
- Coil-coatings
- Plywood
- OEM-Paintwork
- Old paint work



Solid content RFU 98 %
Potlife at 20°C: 35 - 40 min

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

2004/42/IIIB (b)(250)180: The EU limit value for this product (product category: IIB.b) in ready to use form is max. 250 g/l. The VOC content of this product is 180 g/l.



The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

839-7451

Glasurit CV body filler extra slow, light grey



A brand of BASF –
We create chemistry

		100:3 % by weight	
	Mixing Ratio	100 % by weight	839-7451
	Hardener	3 % by weight	G-H-110

Drying Remark

Sandable
20°C 3 - 4 h

Remark

Suitable for large surfaces. Sanding after 3-4h drying.
On galvanized steel: before 839-7451 can be applied it is required to pre-prime the substrate with either Glasurit EP 801-715 (30-40 µm, 45 Min. 60°C) or CV Primer Filler 284-13 (20-25 µm, 20 Min. 60°C). Do not use on acid-hardening products or substrates pre-treated with acid.

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

2004/42/IIIB (b)(250)180: The EU limit value for this product (product category: IIB.b) in ready to use form is max. 250 g/l. The VOC content of this product is 180 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.