923-49





Application:



fire-fighting vehicle

Key Features:

- · suitable for large areas / surfaces
- · brilliant topcoat appearance
- · good leveling
- · excellent UV resistance
- · excellent gloss level

Remarks:

The substrate should be clean, free of dust, rust, oil and grease.

Substrates Glasurit CV - Primer Filler Anodized Aluminium Glasurit CV - Primer **Salvanized steel** Staineless steel Powder coating **JEM-Paintwork** Old paint work Coil-coating = Very well suited Aluminium **3RP / SMC** PP-EPDM Plywood = well suited Wood = suited in some cases



Spreading rate 321 m 2 /l at 1 μ m

Solid Content ~ 39 % (RFU~37%)

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 μm .

The products are suitable for professional use only.

2004/42/IIB (e)(840)612: The EU limit value for this product (product category: IIB.e) in ready

to use form is max. 840 g/l. The VOC content of this product is 612 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

923-49







Mixing Ratio 2:1+10 % by volume



Hardener 929-93, -94



Reducer 352-315, -320, -330



Spray viscosity at 20°C DIN 4: 16-18 s

Potlife at 20°C 8 h

Application:	Compliant - gravity feed cup	🕌 HVLP spray gun	Suction cup	Airless/ Airmix	Pressure pot dblpump
Application pressure	2.2-2.5 bar	2 bar	2.5 bar		
Nozzle size	1.3-1.4	1.3-1.5	1.7		
Number of coats	2	2	2		
Flash off at 20°C	10-15 min	10-15 min	10-15 min		
Film thickness	50-70 μm				

Drying	Overcoatable	Tack-free	Ready for masking	Ready to assemble	Sandable
	Min. Max.				
Object Temp. 20°C	10 h				
Object Temp. 60°C	60 min				

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 μm .

The products are suitable for professional use only.

2004/42/IIB (e)(840)612: The EU limit value for this product (product category: IIB.e) in ready

to use form is max. 840 g/l. The VOC content of this product is 612 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

923-49

Protective clear for daylight paint



Remark

Resistant to UV radiation. Removal of dust nibs or runs only after very good curing. Select hardener and reducer according to ambient temperature and size of object to be painted. IR drying -8 min shortwave, 10 - 15 min medium wave.

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 μm .

The products are suitable for professional use only.

2004/42/IIB (e)(840)612: The EU limit value for this product (product category: IIB.e) in ready

to use form is max. 840 g/l. The VOC content of this product is 612 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.