
924-68

924-68 Variant with 568-409



Application:





busses, sign writing, metallic coating (line 90 CV PLUS), boxes, busses (repair), bus repair

Key Features:

· prevents micro foam during the airless application

· no influence on the surface characteristic

Remarks:

The substrate should be clean, free of dust, rust, oil and grease.

Substrates									Filler						
 = Very well suited = well suited = suited in some cases 	Steel	Galvanized steel	Staineless steel	Aluminium	Anodized Aluminium	GRP / SMC	PP-EPDM	Glasurit CV - Primer	Glasurit CV - Primer Fil / Filler	Powder coating	Coil-coating	Plywood	Mood	OEM-Paintwork	Old paint work

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 μm .

The products are suitable for professional use only.

2004/42/IIB (d)(420)419: The EU limit value for this product (product category: IIB.d) in ready

to use form is max. 420 g/l. The VOC content of this product is 419 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

924-68

924-68 Variant with 568-409





Pre Mix

100% 924-68 + 1 - 3% 568-409 by volume.



Mixing Ratio

3:1:1 by volume



Hardener

922-138, -136, -139



Reducer

352-320, -330, -340



Spray viscosity at 20°C

DIN 4: 18-22 s

Application:	Compliant - gravity feed cup HVLP spray gun	Suction cup Airless/ Airmix Pressure pot dblpump
Application pressure		2 bar
Material pressure		120-180 bar
Nozzle size		0.23-0.28
Voltage		50-80 kV
Elect. Resistance		700-1500 Ω
Number of coats		1.5
Flash off at 20°C		without
Film thickness		40-60 μm

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 μ m.

The products are suitable for professional use only.

2004/42/IIB (d)(420)419: The EU limit value for this product (product category: IIB.d) in ready

to use form is max. 420 g/l. The VOC content of this product is 419 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

924-68

924-68 Variant with 568-409



\bigcirc	Drying	Overco	atable	Tack-free	Ready for masking	Ready to assemble	Sandable	
		Min.	Max.					
	Object Temp. 20°C		16 h	2 h	16 h	12 h	16 h	
	Object Temp. 60°C	30 min		30 min	30 min	30 min	30 min	

Remark

Pre-spray 1 light coat, then apply 1 wet coat for flow. Recoatable with itself for up to 16 hours after application (drying at room temperature).

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 μm .

The products are suitable for professional use only.

2004/42/IIB (d)(420)419: The EU limit value for this product (product category: IIB.d) in ready

to use form is max. 420 g/l. The VOC content of this product is 419 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.