

523-15E Eco Balance

G / Z

Glasurit® Racing Additive



01/2018

Application: Drying accelerator for Glasurit VOC clear 923-610E Eco Balance on vertical surfaces.

Properties: 523-15E Eco Balance increases the chemical reactivity of the products in which it is used, allowing shorter waiting times before sanding, polishing operations or reassembly can be started. 523-15E Eco Balance is particularly suited for body shops that, in order to save energy, bake the applied clear at panel temperatures below 60°C. 523-15E Eco Balance is particularly suitable for small repairs. Improves surface drying and curing performance as well as tape resistance

	Mixing ratio	3 : 1 : 1 100% by vol. 923-610E Eco Balance 33% by vol. 929-61E Eco Balance 33% by vol. 523-15E Eco Balance Mix well and strain before application.
	Spray viscosity DIN 4 at 20°C	18 – 21 s
	Gravity cup Spraying pressure	Refer to the technical data sheet of the product in which 523-15E Eco Balance is used.
	Number of spraycoats	1 ½, without intermediate flash off 2, app. 3 min. intermediate flash off between the application of two spraycoats
		Film thickness: 40 - 60 µm
	Drying at 60 °C Drying at 40 °C Drying at 20 °C	923-610E Eco Balance 10 – 15 min., improved polish ability 30 min. 3 – 4 h

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.



REDcert²-929-35244206

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at <http://techinfo.glasurit.com> or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.