

923-610E Eco Balance

G / C



Glasurit® HS Clear fast-drying VOC

01/2018

Application: HS Clear for 90 Line basecoats. For universal application in quick repair jobs on single panels up to a complete car side.

Properties: Fast drying, excellent polishing behavior.

	Mixing ratio	3 : 1 : 1 100 % by vol. 923-610E Eco Balance 33 % by vol. 929-61E Eco Balance 33 % by vol. 523-15E Eco Balance
	Mixing ratio	Drying at 20 °C 3 : 1 : 1 100 % by vol. 923-610E Eco Balance 33 % by vol. 929-61E Eco Balance 33 % by vol. 523-65E Eco Balance
	Spray viscosity DIN 4 at 20 °C	18 – 21 s Potlife at 20 °C: 45 min.
	Gravity cup Spraying pressure	Compliant gravity-feed spray gun: 1.3 – 1.4 mm 2.0 bar HVLV-gravity-feed spray gun: 1.3 mm 2.0 – 3.0 bar, 0.7 bar at the nozzle
	Number of spraycoats	1 ½ without intermediate flash off 2 app. 3 min. intermediate flash off between the application of two spraycoats Film thickness 40 - 60 µm
	Drying at 60 °C Drying at 40 °C Drying at 20 °C	10 – 15 min. at panel temperature * 30 – 45 min. at panel temperature * 2 – 3 h with 523-65E Eco Balance Glasurit Air-Drying Additive * Drying times can be influenced by the selection of hardener, reducer and application. 523-15E Eco Balance Glasurit Racing Additive can reduce drying times.
	Infrared (short wave)	10 min.

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

The products are suitable for professional use only. It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/IB(d)(420)419: The EU limit value for this product (product category: IIB.d) in ready to use form is max 420 g/litre of VOC.
The VOC content of this product is 419 g/litre.



REDcert²-929-35244206

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at <http://techinfo.glasurit.com> or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.