839-20

Multi Purpose Body Filler, white Variant for CV

Glasurit®

A brand of BASF –
We create chemistry

Application:	all applications
Key Features:	• fast drying • suitable on all substrates • good filling properties • fast sandable
Remarks:	The substrate should be clean, free of dust, rust, oil and grease. Solid Content ~ 96 %

Handling

Substrates
Very well suited:

• Steel

• Galvanized Steel

• Aluminium

Well suited:

• GRP / SMC

• Glasurit CV - Primer Filler / Filler

• Powder coating

• Coil-coating

• Plywood

• Wood

• OEM-Paintwork

• Old paint work

Suited in some cases:

• Stainless steel

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 μm.

The products are suitable for professional use only.

2004/42/IIB (b)(250)180: The EU limit value for this product (product category: IIB.b) in ready

to use form is max. 250 g/l. The VOC content of this product is 180 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

839-20

Multi Purpose Body Filler, white Variant for CV

100 : 2-3 % by weight

Hardener 948-36

Spray viscosity at 20°C DIN 4: **Potlife at 20°C** 4 min

Drying at 20°C 20-30 min

Remark Can be sanded after 20 - 30 min.
Not suitable for applications that require elasticity, e.g., weld seams.
Do not use on acid-hardening products or substrates pre-treated with acid.

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

2004/42/IIB (b)(250)180: The EU limit value for this product (product category: IIB.b) in ready
to use form is max. 250 g/l. The VOC content of this product is 180 g/l.

BASF Coatings GmbH - Automotive Refinish Coatings Solutions Europe - Glasuritstrasse 1 - 48165 Münster - Germany   07/2021

Page 2 of 2