


# 922-138

CV topcoat hardener normal



A brand of BASF –  
We create chemistry

**Application:**



**Key Features:**

Hardener may only be used in HS 2K CV topcoat 68 / 58, RAL 9006, 568-46 and CV clear coats 924-68 and 924-168. Find additional information in the technical data sheet of the topcoat.

**Remarks:**

Carefully close the container after removal of the hardener.  
Isocyanate hardeners are sensitive to moisture.

**Substrates**

- = Very well suited
- = well suited
- = suited in some cases

Steel	Galvanized steel	Stainless steel	Aluminium	Anodized Aluminium	GRP / SMC	PP-EPDM	Glasurit CV - Primer	Glasurit CV - Primer Filler / Filler	Powder coating	Coil-coating	Plywood	Wood	OEM-Paintwork	Old paint work
-------	------------------	-----------------	-----------	--------------------	-----------	---------	----------------------	--------------------------------------	----------------	--------------	---------	------	---------------	----------------

**Solid Content** 90 %



**Drying**

**Overcoatable**

**Tack-free**

**Ready for masking**

**Ready to assemble**

**Sandable**

Min. Max.

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

**Safety advice:**

It cannot be ruled out that this product contains particles < 0.1 µm

The products are suitable for professional use only.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at [www.glasurit.com](http://www.glasurit.com) or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.