1006-26

UP Spray Filler, grey Variant for CV



Application:

all applications

Key Features:

· good filling properties

fast drying

· fast sandable

Remarks:

The substrate should be clean, free of dust, rust, oil and grease.

Max 2% 352-310 (by weight).

Handling

Substrates

Very well suited:

- · GRP / SMC
- Wood
- · OEM-Paintwork
- Old paint work
 Well suited:



- Steel
- Aluminium
- · Glasurit CV Primer Filler / Filler
- · Coil-coating
- · Powder coating
- Plywood



Spreading rate 551 m²/l at 1 μ m Solid Content 72 % (RFU~73%)



Suction cup

Application pressure 2.5 bar Nozzle size 2.5-3 Number of coats 3-8

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 μm .

The products are suitable for professional use only.

2004/42/IIB (b)(250)249: The EU limit value for this product (product category: IIB.b) in ready

to use form is max. 250 g/l. The VOC content of this product is 249 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

BASF Coatings GmbH - Automotive Refinish Coatings Solutions Europe - Glasuritstrasse 1 - 48165 Münster - Germany

1006-26

UP Spray Filler, grey Variant for CV



100:5% by volume

Hardener 948-22

Reducer 352-310 max. 2%

S

Spray viscosity at 20°C DIN 4: Potlife at 20°C 30 min

Application: Compliant gravity-feed spray gun

Application pressure bar 2.2-2.5

Nozzle size 2.5-3

Number of spray coats 3-8

Film thickness µm >200 max. 1000

 \odot

Remark

Drying at 20°C 3-4 h

Drying at 60°C 30 min

Sandable

Drying Remark Object Temp. 20 °C 3-4 h

Object Temp. 60 °C 30 min

Do not overcoat etch wash primer or acid pre treated substrates with 1006-26!

Use only dry sanding for 1006-26. Galvanized steel must be primed with 283-6150 (10 - 15 μ m) and

 $284\text{-}13~(\text{max.}~30\text{-}40~\mu\text{m}).$ For temperature less than 15°C or to speed up the drying the amount of

948-22 can be increased up to 7.5 vol.%.

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 μm .

The products are suitable for professional use only.

2004/42/IIB (b)(250)249: The EU limit value for this product (product category: IIB.b) in ready

to use form is max. 250 g/l. The VOC content of this product is 249 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

1006-26

UP Spray Filler, grey Variant for CV



Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 μm .

The products are suitable for professional use only.

2004/42/IIB (b)(250)249: The EU limit value for this product (product category: IIB.b) in ready

to use form is max. 250 g/l. The VOC content of this product is 249 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

BASF Coatings GmbH - Automotive Refinish Coatings Solutions Europe - Glasuritstrasse 1 - 48165 Münster - Germany