




A brand of BASF –
We create chemistry

1109-1240/4

Underbody protection, black

Application:



structure effect, underbody protection

Key Features:

- can be used on all Glasurit PU and EP CV primer fillers and fillers
- high flexible
- outstanding application characteristics

Remarks:

The substrate should be clean, free of dust, rust, oil and grease.

Substrates

- = Very well suited
- = well suited
- = suited in some cases

Steel	Galvanized steel	Stainless steel	Aluminium	Anodized Aluminium	GRP / SMC	PP-EPDM	Glasurit CV - Primer	Glasurit CV - Primer Filler / Filler	Powder coating	Coil-coating	Plywood	Wood	OEM-Paintwork	Old paint work
								●●					●●	●●



Spreading rate 379 m²/l at 1 µm

Solid Content ~ 55 %

Handling



Protect from frost.

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

2004/42/IIIB (e)(840)32: The EU limit value for this product (product category: IIB.e) in ready to use form is max. 840 g/l. The VOC content of this product is 32 g/l.






The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.



A brand of BASF –
We create chemistry

1109-1240/4

Underbody protection, black

Application:	 Compliant - gravity feed cup	 HVLP spray gun	 Suction cup	 Airless/ Airmix	 Pressure pot dbl.-pump
Application pressure	bar	2-2.5	2-2.5	2-4	2.5
Nozzle pressure	bar			120-180	2
Nozzle size		3-4	3-5	0.41-0.5	3-4
Number of coats		2-6	4-6	2-6	2-6
Film thickness	µm	500 - 1000			

 Drying	Overcoatable	Tack-free	Ready for masking	Ready to assemble	Sandable
Object Temp. 20°C	Min. Max.				
	6 h				

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

2004/42/IIIB (e)(840)32: The EU limit value for this product (product category: IIB.e) in ready to use form is max. 840 g/l. The VOC content of this product is 32 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.