


# 284-13

284-13 Variant for rough-blasted substrates (5:1:1)



A brand of BASF –  
We create chemistry

**Application:**



chassis painting, container, construction machinery (steel), steel and galvanized steel spare parts

**Key Features:**

- for rough-blasted substrates

**Remarks:**

The substrate should be clean, free of dust, rust, oil and grease.  
Aluminum-Chassis have to be primed with a suitable primer.

**Substrates**

- = Very well suited
- = well suited
- = suited in some cases

Steel	Galvanized steel	Stainless steel	Aluminium	Anodized Aluminium	GRP / SMC	PP-EPDM	Glasurit CV - Primer	Glasurit CV - Primer Filler / Filler	Powder coating	Coil-coating	Plywood	Wood	OEM-Paintwork	Old paint work
●●	●				●●		●●		●	●	●●	●●	●	●●



**Mixing Ratio**

5 : 1 : 1 by volume



**Hardener**

922-18 Pro, -16 Pro



**Reducer**

352-320, -330, -340

**Potlife at 20°C**

2 h

**Safety advice:**

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

**2004/42/IIIB (c I)(540)508:** The EU limit value for this product (product category: IIB.c I) in ready to use form is max. 540 g/l. The VOC content of this product is 508 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at [www.glasurit.com](http://www.glasurit.com) or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

# 284-13

284-13 Variant for rough-blasted substrates (5:1:1)



A brand of BASF –  
We create chemistry

Application:	Compliant - gravity feed cup	HVLV spray gun	Suction cup	Airless/ Airmix	Pressure pot dbl.-pump	
Application pressure	bar	2.2-2.5	2	2.5	2	2.5
Material pressure	bar				120-150	0.8-1.5
Nozzle size		1.6-1.8	1.5-1.7	1.5-1.7	0.28-0.33	1-1.1
Voltage	kV				50-80	
Elect. Resistance	Ω				300-500	
Number of coats		2	2	2	1-2	2
Flash off at 20°C	min	without	without	without	without	without
Film thickness	µm	60-70				

Drying	Overcoatable		Tack-free	Ready for masking	Ready to assemble	Sandable
	Min.	Max.				
Object Temp. 20°C	60 min	72 h	2 h	16 h	16 h	16 h
Object Temp. 60°C	30 min		30 min	30 min	30 min	45 min

**Remark**

Can be tinted with up to 10% of 68 line topcoat for the 2nd spray coat.  
 To plasticize the product, see variant with 522-111 Softface additive.  
 Can be overcoated with CV topcoats of lines 68, 58, 55.\*  
 For tinting see variant with CV Primer Tinting Paste 568-408.  
 On hot-dip galvanized steel, adhesion must be tested beforehand.  
 \* Has to be applied within 72h with 68 line, within one working day with 55 line.

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

**Safety advice:**

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

**2004/42/IIIB (c I)(540)508:** The EU limit value for this product (product category: IIB.c I) in ready to use form is max. 540 g/l. The VOC content of this product is 508 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at [www.glasurit.com](http://www.glasurit.com) or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.