




TECHNICAL INFORMATION

568-407 Glasurit CV Brush and Roll Additive

Z

Range of application:



all applications

Performance:

- allows application of the top coat with brush or roller
- suitable on all Glasurit CV primer filler and filler
- good leveling

Special remarks:

It cannot be ruled out that this product contains particles < 0.1 µm
The products are suitable for professional use only.

Remarks:

The substrate should be clean, free of dust, rust, oil and grease



Painting process

Spreading rate

Solid content 5 %



Mixing ratio

4 : 1 : 5 - 15% by volume



Hardeners

922-138, 922-136 or 922-139



Reducer

568-407



Viscosity
DIN 4 / 20° C

Potlife 20 °C

60 min.



Drying



Over-coatable



Tack-free



Ready for masking



Ready to assemble



Sandable

min max

Object temp.

20°C

3 h

16 h

2.5 h

16 h

12 h

16 h

Object temp.

60°C

30 min.

30 min.

30 min.

30 min.

30 min.

Remarks



2-3 applications with brush or roll. Intermediate drying 3 h 20°C

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.