



TECHNICAL INFORMATION

922-139/-138/-136 Glasurit 2K CV Topcoat Hardener
922-139 slow Premium, 922-138 normal, 922-136 fast

Z

Range of application:



all applications

Performance:

Special remarks:

It cannot be ruled out that this product contains particles < 0.1 µm
The products are suitable for professional use only.

Remarks:

Find addition information in the technical data sheet of the top coat



Painting process

Spreading rate

Solid content 90 %

Remarks



Hardener may only be used in HS 2K CV topcoat 68 / 58, RAL 9006, 568-46 and CV clearcoats 924-68 and 924-168.
922-139 in topcoat and clearcoat: at least 45 - 60 min. 60°C
Carefully close the container after removal of the hardener.
Isocyanate hardeners are sensitive to moisture.