


284-13

284-13 Variant with 568-408



A brand of BASF –
We create chemistry

Application:



chassis painting, container, construction machinery (steel), steel and galvanized steel spare parts

Key Features:

- suitable on all Glasurit CV primer
- suitable for large areas / surfaces
- very good corrosion protection
- good coverage of shot blasted profile
- brilliant top coat appearance
- outstanding application characteristics
- tintable

Remarks:

The substrate should be clean, free of dust, rust, oil and grease.
Aluminum-Chassis have to be primed with a suitable primer.

Substrates

- = Very well suited
- = well suited
- = suited in some cases

●●	Steel	●	Galvanized steel		Stainless steel		Aluminium		Anodized Aluminium	●●	GRP / SMC		PP-EPDM	●●	Glasurit CV - Primer	●●	Glasurit CV - Primer Filler / Filler	●	Powder coating	●	Coil-coating	●●	Plywood	●●	Wood	●	OEM-Paintwork	●●	Old paint work
----	-------	---	------------------	--	-----------------	--	-----------	--	--------------------	----	-----------	--	---------	----	----------------------	----	--------------------------------------	---	----------------	---	--------------	----	---------	----	------	---	---------------	----	----------------

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

2004/42/IIIB (c I)(540)508: The EU limit value for this product (product category: IIB.c I) in ready to use form is max. 540 g/l. The VOC content of this product is 508 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

284-13

284-13 Variant with 568-408



A brand of BASF –
We create chemistry



Pre Mix

max. 10% 568-408 by volume



Mixing Ratio

4 : 1 : 1 by volume



Hardener

922-18 Pro, -16 Pro



Reducer

352-320, -330, -340



Spray viscosity at 20°C

DIN 4: 25 s

Potlife at 20°C

2 h

Application:		Compliant - gravity feed cup	HVLV spray gun	Suction cup	Airless/ Airmix	Pressure pot dbl.-pump
Application pressure	bar	2.2-2.5	2	2.5	2	2.5
Material pressure	bar				120-150	0.8-1.5
Nozzle size		1.6-1.8	1.5-1.7	1.5-1.7	0.28-0.33	1-1.1
Voltage	kV				50-80	
Elect. Resistance	Ω				300-500	
Number of coats		2	2	2	1-2	2
Flash off at 20°C	min	without	without	without	without	without
Film thickness	µm	60-70				

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

2004/42/IIIB (c I)(540)508: The EU limit value for this product (product category: IIB.c I) in ready to use form is max. 540 g/l. The VOC content of this product is 508 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

284-13

284-13 Variant with 568-408



A brand of BASF –
We create chemistry



Drying

	Overcoatable		Tack-free	Ready for masking	Ready to assemble	Sandable
	Min.	Max.				
Object Temp. 20°C	60 min	72 h	2 h	16 h	16 h	16 h
Object Temp. 60°C	30 min		30 min	30 min	30 min	45 min

Remark

Can be tinted with up to 10% of 68 line topcoat for the 2nd spray coat.
 To plasticize the product, mix it 4 : 1 by volume with 522-111 Softface Additive before adding hardener.
 Can be overcoated with CV topcoats of lines 68, 58, 55.*
 Mixing ratio 5:1:1 by vol. = higher viscosity, e. g. for rough-blasted substrates.
 On hot-dip galvanized steel, adhesion must be tested beforehand.
 * Has to be applied within 72h with 68 line, within one working day with 55 line.
 With UP spray filler apply 1 full coat ~30-40 µm.

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

2004/42/IIIB (c I)(540)508: The EU limit value for this product (product category: IIB.c I) in ready to use form is max. 540 g/l. The VOC content of this product is 508 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.