

285-0 CV

Transparent-Sealer CV, clear



A brand of BASF –
We create chemistry

Application:



sign writing, cabs (color change), multi - color painting, powder coated profiles / boxes

Key Features:

- tintable
- brilliant top coat appearance
- fast drying

Remarks:

The substrate should be clean, free of dust, rust, oil and grease.

Substrates

- = Very well suited
- = well suited
- = suited in some cases

| | | | | | | | | | | | | | | |
|-------|------------------|-----------------|-----------|--------------------|-----------|---------|----------------------|--------------------------------------|----------------|--------------|---------|------|---------------|----------------|
| Steel | Galvanized steel | Stainless steel | Aluminium | Anodized Aluminium | GRP / SMC | PP-EPDM | Glasurit CV - Primer | Glasurit CV - Primer Filler / Filler | Powder coating | Coil-coating | Plywood | Wood | OEM-Paintwork | Old paint work |
| ●● | ●● | ●● | ●● | ●● | ○ | ●● | ●● | ●● | ●● | ●● | ○ | ●● | ●● | ●● |



Spreading rate 406 m²/l at 1 µm

Solid Content ~ 66 % (RFU~53%)

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

2004/42/IIIB (c II)(540)502: The EU limit value for this product (product category: IIB.c II) in ready to use form is max. 540 g/l. The VOC content of this product is 502 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

285-0 CV

Transparent-Sealer CV, clear



A brand of BASF –
We create chemistry



Mixing Ratio 2:1+30 % by volume



Hardener 922-18 Pro, -16 Pro



Reducer 352-310, -315, -320



Spray viscosity at 20°C DIN 4: 19-21 s

Potlife at 20°C 3 h

| Application: | Compliant - gravity feed cup | HVLV spray gun | Suction cup | Airless/ Airmix | Pressure pot dbl.-pump |
|---------------------------------|------------------------------|----------------|-------------|-----------------|------------------------|
| Application pressure bar | 2.2-2.5 | 2 | 2.5 | | |
| Nozzle size | 1.4 | 1.5 | 1.7 | | |
| Number of coats | 1 | 1 | 1 | | |
| Film thickness µm | 20-25 | | | | |



| Drying | Overcoatable | Tack-free | Ready for masking | Ready to assemble | Sandable |
|--------------------------|--------------|-----------|-------------------|-------------------|----------|
| | Min. Max. | | | | |
| Object Temp. 20°C | 15 min 2 h | | | | |

Remark Transparent Sealer 285-0 CV can be tinted with (up to 10% of) 68 line topcoat.

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

2004/42/IIIB (c II)(540)502: The EU limit value for this product (product category: IIB.c II) in ready to use form is max. 540 g/l. The VOC content of this product is 502 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.