




A brand of BASF –  
We create chemistry

# 568-46

568-46 Variant one layer system

**Application:**



chassis painting, chassis (color change), container

**Key Features:**

- tintable
- suitable for large areas / surfaces
- good leveling
- can be applied directly on steel or galvanized steel
- high efficiency
- good corrosion protection

**Remarks:**

Aluminum-Chassis have to be primed with a suitable primer.  
The substrate should be clean, free of dust, rust, oil and grease.

**Substrates**

- = Very well suited
- = well suited
- = suited in some cases

●●	Steel	●●	Galvanized steel	●	Stainless steel		Aluminium		●	Anodized Aluminium		●	GRP / SMC			PP-EPDM		●	Glasurit CV - Primer		●	Glasurit CV - Primer Filler / Filler		●	Powder coating			Coil-coating			Plywood			Wood		●	OEM-Paintwork		●	Old paint work
----	-------	----	------------------	---	-----------------	--	-----------	--	---	--------------------	--	---	-----------	--	--	---------	--	---	----------------------	--	---	--------------------------------------	--	---	----------------	--	--	--------------	--	--	---------	--	--	------	--	---	---------------	--	---	----------------

**Safety advice:**

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

**2004/42/IIIB (c II)(540)530:** The EU limit value for this product (product category: IIB.c II) in ready to use form is max. 540 g/l. The VOC content of this product is 530 g/l.






The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at [www.glasurit.com](http://www.glasurit.com) or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.






# 568-46

568-46 Variant one layer system



A brand of BASF –  
We create chemistry

	<b>Pre Mix</b>	568-46 with AD 68 mix 568-46 with line 68 in the ratio 1 : 1
	<b>Mixing Ratio</b>	7:1+10-15% by volume
	<b>Hardener</b>	922-138, -136, -139
	<b>Reducer</b>	352-315, -320, -330
	<b>Spray viscosity at 20°C</b>	DIN 4: 30-40 s
	<b>Potlife at 20°C</b>	2 h

Application:		<b>Compliant - gravity feed cup</b>		<b>HVLV spray gun</b>		<b>Suction cup</b>		<b>Airless/ Airmix</b>		<b>Pressure pot dbl.-pump</b>
<b>Application pressure</b>	bar	2.2-2.5		2		2		2		2.5
<b>Material pressure</b>	bar							120-150		0.8-1.5
<b>Nozzle size</b>		1.6-1.8		1.7-1.9		1.7-1.9		0.28-0.33		1-1.3
<b>Voltage</b>	kV							50-80		
<b>Elect. Resistance</b>	Ω							700-1500		
<b>Number of coats</b>		2		2		2		1-2		2
<b>Flash off at 20°C</b>	min	10-15		10-15		10-15		10-15		10-15
<b>Film thickness</b>	µm	70-100								

**Safety advice:**

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

**2004/42/IIIB (c II)(540)530:** The EU limit value for this product (product category: IIB.c II) in ready to use form is max. 540 g/l. The VOC content of this product is 530 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at [www.glasurit.com](http://www.glasurit.com) or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

# 568-46

568-46 Variant one layer system



A brand of BASF –  
We create chemistry



## Drying

	Overcoatable	Tack-free	Ready for masking	Ready to assemble	Sandable
	Min.	Max.			
Object Temp. 20°C		16 h	2 h	16 h	16 h
Object Temp. 60°C	30 min		30 min	30 min	30 min

## Remark

The shelf life of the mixed product (line 68 topcoat and 568 - 46) is only 2 weeks.  
The DTM version is not suitable for areas that are directly exposed to sunlight.  
The corrosion protection can only be achieved, if the required film thickness is applied (covering of sand blasting roughness, edges). Mixing of 568-46 can change the color.  
The adhesion on hot dipped galvanized steel has to be checked before.

## Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

**2004/42/IIIB (c II)(540)530:** The EU limit value for this product (product category: IIB.c II) in ready to use form is max. 540 g/l. The VOC content of this product is 530 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at [www.glasurit.com](http://www.glasurit.com) or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.