




A brand of BASF –  
We create chemistry

# 58-MAN 9011

2K HS CV chassis topcoat, black, satin gloss

**Application:**



all applications where a reduced gloss is required, chassis (color change), chassis painting, container

**Key Features:**

- suitable on all Glasurit CV primer filler and filler
- good leveling
- high efficiency
- good hiding power
- excellent surface hardness
- excellent UV resistance

**Remarks:**

The substrate should be clean, free of dust, rust, oil and grease.

**Substrates**

- = Very well suited
- = well suited
- = suited in some cases

Steel	Galvanized steel	Stainless steel	Aluminium	Anodized Aluminium	GRP / SMC	PP-EPDM	Glasurit CV - Primer	Glasurit CV - Primer Filler / Filler	Powder coating	Coil-coating	Plywood	Wood	OEM-Paintwork	Old paint work
								●●					○	○



**Spreading rate** 536 m<sup>2</sup>/l at 1 µm

**Solid Content** ~ 67 %

**Safety advice:**

It cannot be ruled out that this product contains particles < 0.1 µm

The products are suitable for professional use only.

**2004/42/IIIB (d)(420)419:** The EU limit value for this product (product category: IIB.d) in ready to use form is max. 420 g/l. The VOC content of this product is 419 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at [www.glasurit.com](http://www.glasurit.com) or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.



A brand of BASF –  
We create chemistry

# 58-MAN 9011

2K HS CV chassis topcoat, black, satin gloss



**Mixing Ratio** 4 : 1 : 1 by volume



**Hardener** 922-139, -138, -136



**Reducer** 352-320, -315, -330



**Spray viscosity at 20°C** DIN 4: 18-22 s

**Potlife at 20°C** 1.5 h

Application:		Compliant - gravity feed cup	HVLV spray gun	Suction cup	Airless/ Airmix	Pressure pot dbl.-pump
<b>Application pressure</b>	bar	2.2-2.5	2	2.5	2	2.5
<b>Material pressure</b>	bar				120-180	0.8-1.5
<b>Nozzle size</b>		1.4	1.5	1.7	0.23-0.28	1-1.1
<b>Voltage</b>	kV				50-80	
<b>Elect. Resistance</b>	Ω				700-1500	
<b>Number of coats</b>		1.5	1.5	1.5	1.5	1.5
<b>Flash off at 20°C</b>	min	without	without	without	without	without
<b>Film thickness</b>	µm	40-60				

**Safety advice:**

It cannot be ruled out that this product contains particles < 0.1 µm

The products are suitable for professional use only.

**2004/42/IIIB (d)(420)419:** The EU limit value for this product (product category: IIB.d) in ready to use form is max. 420 g/l. The VOC content of this product is 419 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at [www.glasurit.com](http://www.glasurit.com) or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

# 58-MAN 9011

2K HS CV chassis topcoat, black, satin gloss



A brand of BASF –  
We create chemistry



## Drying

	Overcoatable	Tack-free	Ready for masking	Ready to assemble	Sandable
	Min.	Max.			
Object Temp. 20°C		16 h	2.5 h	16 h	16 h
Object Temp. 60°C	30 min		30 min	30 min	30 min

## Remark

Gloss level is depending on the specific color master.  
Recoatable with itself without intermediate sanding for up to 16 hours after application.  
Due to the reduced gloss level not suitable for blend in processes.

## Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm

The products are suitable for professional use only.

**2004/42/IIIB (d)(420)419:** The EU limit value for this product (product category: IIB.d) in ready to use form is max. 420 g/l. The VOC content of this product is 419 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at [www.glasurit.com](http://www.glasurit.com) or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.