




A brand of BASF –
We create chemistry

58-MB 9124

2K HS CV chassis topcoat, chassis black, satin gloss

Application:



all applications where a reduced gloss is required, chassis (color change), chassis painting, container

Key Features:

- suitable on all Glasurit CV primer filler and filler
- good leveling
- high efficiency
- good hiding power
- excellent surface hardness
- excellent UV resistance

Remarks:

The substrate should be clean, free of dust, rust, oil and grease.

Substrates

- = Very well suited
- = well suited
- = suited in some cases

Steel	Galvanized steel	Stainless steel	Aluminium	Anodized Aluminium	GRP / SMC	PP-EPDM	Glasurit CV - Primer	Glasurit CV - Primer Filler / Filler	Powder coating	Coil-coating	Plywood	Wood	OEM-Paintwork	Old paint work
								●●					○	○



Spreading rate 536 m²/l at 1 µm

Solid Content ~ 67 %

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm

The products are suitable for professional use only.

2004/42/IIIB (d)(420)419: The EU limit value for this product (product category: IIB.d) in ready to use form is max. 420 g/l. The VOC content of this product is 419 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

58-MB 9124

2K HS CV chassis topcoat, chassis black, satin gloss



A brand of BASF –
We create chemistry



Mixing Ratio 4 : 1 : 1 by volume



Hardener 922-139, -138, -136



Reducer 352-320, -315, -330



Spray viscosity at 20°C DIN 4: 18-22 s

Potlife at 20°C 1.5 h

Application:		Compliant - gravity feed cup	HVLV spray gun	Suction cup	Airless/ Airmix	Pressure pot dbl.-pump
Application pressure	bar	2.2-2.5	2	2.5	2	2.5
Material pressure	bar				120-180	0.8-1.5
Nozzle size		1.4	1.5	1.7	0.23-0.28	1-1.1
Voltage	kV				50-80	
Elect. Resistance	Ω				700-1500	
Number of coats		1.5	1.5	1.5	1.5	1.5
Flash off at 20°C	min	without	without	without	without	without
Film thickness	µm	40-60				

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm

The products are suitable for professional use only.

2004/42/IIIB (d)(420)419: The EU limit value for this product (product category: IIB.d) in ready to use form is max. 420 g/l. The VOC content of this product is 419 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

58-MB 9124

2K HS CV chassis topcoat, chassis black, satin gloss



A brand of BASF –
We create chemistry



Drying

Overcoatable

Tack-free

Ready for masking

Ready to assemble

Sandable

Min. Max.

Object Temp. 20°C

16 h

2.5 h

16 h

12 h

16 h

Object Temp. 60°C

30 min

30 min

30 min

30 min

30 min

Remark

Gloss level is depending on the specific color master.
Recoatable with itself without intermediate sanding for up to 16 hours after application.
Due to the reduced gloss level not suitable for blend in processes.

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm

The products are suitable for professional use only.

2004/42/IIIB (d)(420)419: The EU limit value for this product (product category: IIB.d) in ready to use form is max. 420 g/l. The VOC content of this product is 419 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.