
## 839-45





Application:





all applications

**Key Features:** 

- · suitable for large areas / surfaces
- · high flexible alignment for welding seams
- · long pot life
- · temperature resistance up to 180°C

Remarks:

The substrate should be clean, free of dust, rust, oil and grease.

Substrates									Filler						
<ul> <li>= Very well suited</li> <li>= well suited</li> <li>= suited in some cases</li> </ul>	• Steel	Galvanized steel	Staineless steel	• Aluminium	Anodized Aluminium	GRP / SMC	PP-EPDM	Glasurit CV - Primer	Glasurit CV - Primer Fi	<ul> <li>Powder coating</li> </ul>	Coil-coating	• Plywood	pood •	<ul><li>OEM-Paintwork</li></ul>	Old paint work

Solid Content

~ 98 %

### Safety advice:

It cannot be ruled out that this product contains particles < 0.1  $\mu m$ .

The products are suitable for professional use only.

2004/42/IIB (b)(250)180: The EU limit value for this product (product category: IIB.b) in ready

to use form is max. 250 g/l. The VOC content of this product is 180 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

# 839-45

CV Flexible Body Filler, light grey





**Mixing Ratio** 

100:3% by weight



Hardener

948-36

Potlife at 20°C

20 min



**Drying** 

Overcoatable

Tack-free

Ready for masking Ready to assemble

Sandable

Min. Max.

Object Temp. 20°C

2.5 h

Sandable after 2,5 hours.

#### Remark

Highly flexible product, for example for weld seams on tankers. Temperature resistant up to 180°C. On zinc, before body-filling, see variant with EP 801-705 CV Primer Filler or variant with 284-13 CV primer filler.

Do not use on wash primer or acid-pre-treated surfaces!

#### Safety advice:

It cannot be ruled out that this product contains particles < 0.1  $\mu m$ .

The products are suitable for professional use only.

2004/42/IIB (b)(250)180: The EU limit value for this product (product category: IIB.b) in ready

to use form is max. 250 g/l. The VOC content of this product is 180 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.