


924-168

HS 2K CV Bus Clear



A brand of BASF –
We create chemistry

Application:



metallic coating, topcoat 90 line CV PLUS, bus repair, busses

Key Features:

- suitable for large areas / surfaces
- good leveling
- excellent UV resistance
- excellent gloss level

Remarks:

The substrate should be clean, free of dust, rust, oil and grease.

Substrates

- = Very well suited
- = well suited
- = suited in some cases

Steel	Galvanized steel	Stainless steel	Aluminium	Anodized Aluminium	GRP / SMC	PP-EPDM	Glasurit CV - Primer	Glasurit CV - Primer Filler / Filler	Powder coating	Coil-coating	Plywood	Wood	OEM-Paintwork	Old paint work
-------	------------------	-----------------	-----------	--------------------	-----------	---------	----------------------	--------------------------------------	----------------	--------------	---------	------	---------------	----------------



Spreading rate 510 m²/l at 1 µm

Solid Content ~ 61 % (RFU~56%)

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

2004/42/IIIB (d)(420)419: The EU limit value for this product (product category: IIB.d) in ready to use form is max. 420 g/l. The VOC content of this product is 419 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

924-168

HS 2K CV Bus Clear



A brand of BASF –
We create chemistry

	Mixing Ratio	3 : 1 : 1 by volume
	Hardener	922-136, -138, -139
	Reducer	352-330
	Spray viscosity at 20°C	DIN 4: 18-20 s
	Potlife at 20°C	1.5 h

Application:	Compliant - gravity feed cup	HVLV spray gun	Suction cup	Airless/ Airmix	Pressure pot dbl.-pump
Application pressure	bar	2.2-2.5	2	2.5	2.5
Nozzle pressure	bar				0.8-1.5
Nozzle size		1.2-1.4	1.3-1.5	1.7	1-1.1
Voltage	kV				50-80
Number of coats		2	2	2	2
Flash off at 20°C	min	10-15	10-15	10-15	10-15
Film thickness	µm	40-60			

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

2004/42/IIIB (d)(420)419: The EU limit value for this product (product category: IIB.d) in ready to use form is max. 420 g/l. The VOC content of this product is 419 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

924-168

HS 2K CV Bus Clear



A brand of BASF –
We create chemistry



Drying

	Overcoatable		Tack-free	Ready for masking	Ready to assemble	Sandable
	Min.	Max.				
Object Temp. 20°C		16 h	2 h	16 h	12 h	16 h
Object Temp. 60°C	30 min		30 min	30 min	30 min	30 min

Remark

Pre-spray 1 light coat, then apply 1 wet coat for flow. Recoatable with itself for up to 16 hours after application of first coat, after force drying and 16 h at 20°C the adhesion promoter 285-0 CV has to be sprayed first.

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

2004/42/IIIB (d)(420)419: The EU limit value for this product (product category: IIB.d) in ready to use form is max. 420 g/l. The VOC content of this product is 419 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.